



AREAS OF USE

Multiple general usage in home or industrial applicactions

Also for industrial use

- Standard quality with a smooth face
- Natural Fibre Board
- Multipurpose board for DIY, furniture, packaging and temporary structures
- Robust packing for protection and flatness

# 5/2019 Valid to subsequent revisions

# | PRODUCT RANGE AND PACKAGING

Туре	Thickness [mm]	Pieces/Pack	Standard sizes [mm×mm]	Coverage/Pallet [m²]	Weight/Pallet [kg]
HB	3.0	150	1220×2440	446.52	1205.60
general purpose	6.0	75	1220×2440	223.26	1205.60

# | TECHNICAL SPECIFICATION

### STEICO Hardboard – EN 622-2. Type HB

Property	Unit	Thickness [mm]		
		2.5 mm ≤ t ≤ 3.5 mm	3.5 < t ≤ 5.5 mm	t > 5.5 mm
Bending strength	N/mm²	30	30	25
Internal bond	N/mm²	0.50	0.50	0.50
Swelling in thickness	%	37	30	25

# | OTHER PROPERTIES

Thickness tolerances at the time of dispatch from the factory – EN 622-1

Property	Unit	Thickness [mm]		
		2.5 mm ≤ t ≤ 3.5 mm	$3.5 \text{ mm} \leq t \leq 5.5 \text{ mm}$	t > 5.5 mm
Tolerance	mm	± 0.3	± 0.5	± 0.7

General properties at the time of dispatch from the factory – EN 622-1

Property	Limit	
Dimensional tolerances	± 2 mm/m; max ± 5 mm	
Squareness	2 mm/m	
Edge straightness	1.5 mm/m	
Moisture content	4 – 9 %	

- Fire class according to EN 13501-1: Class E
- The edges are butt jointed







Quality Management ISO 9001:2015



Your STEICO Distibutor