



- Particularly robust and durable
- Excellent insulation properties in winter and summer
- Both water repellent and vapour permeable for robust constructions
- Large variety of formats and thicknesses from 40 to 240mm
- Suitable for air-injected insulation from 40mm thick
- Available in large format boards for off-site construction
- Extensive catalogue of construction details available
- Manufactured with fresh softwood - sustainable climate protection through CO₂ storage

Application area



- Soffit panel for the STEICO *secure* ETICS

Technical data

Produced and supervised according to	EN 13171, EN 14964
Board designation	WF EN 13171 – T5 – DS(70/90)3 – CS (10\Y)150 –TR20(30) – WS1,0 – MU5
Fire class (RTF) according to EN 13501-1	E
Permanent temperature range [°C]	≤100
Declared thermal conductivity [W/(m*K)]	Type H: 0.048
Density [kg/m ³]	Type H: approx. 265; Type H dry: approx. 180
Specific heat capacity [J/(kg*K)]	2,100
Compression strength [kPa]	150
Tensile strength perpendicular to face [kPa]	20
Manufacturing process	wet process / utilisation of the wood's own lignin for panel bonding
Ingredients	wood fibre, aluminium sulphate, paraffin, bond between layers
European Waste Code (EWC)	030105/170201, disposal as wood and wood-based materials, waste wood category A II
Outdoor exposure	4 weeks
Bonded carbon [kg CO ₂ equivalent./m ³]	Typ H: 400; Typ H dry: 260

Additional technical data

Thickness [mm]	Type	Declared thermal resistance [(m ² *K)/W]	s _d value [m]
20	H	0.40	0.10

Forms of delivery

Thickness [mm]	Type	Edge profile	Length [mm]	Width [mm]	Number/pal. [pcs.]	Number/pack. [pcs.]	Coverage/pal. gross [m ²]
20	H	SE	1350	500	112	6	75.600

Weight and packing

Thickness [mm]	Type	Edge profile	Length [mm]	Width [mm]	Weight/m ² [kg]	Weight/pcs. [kg]	Weight/pack. [kg]	Packaging/pack. Paper/cardboard (approx.) [kg]
20	H	SE	1350	500	5.00	3.4	23.00	1.20

Notes

Storage

- Store wood fibre boards horizontally, flat and dry
- Protect edges from damage
- Only remove the film packaging when the ambient climate is dry and keep the pallet packing label
- Maximum stacking height: 2 pallets

Disposal

- Disposal of off-cuts: Waste code (EAK / AVV) 170201/030105, such as wood and wood-based materials, waste wood category II
- Disposal after dismantling: Waste code (EAK / AVV) 170201/030105, like wood and wood-based materials, waste wood category II

Cutting

- The boards can be cut to size using the STEICO *isoflex cut combi* cutting table or a band saw, circular saw, jigsaw and other wood-cutting tools.

Occupational health and safety

- Comply with local regulations for the processing of wood-fibre material
- Suitable protective measures must be taken when cutting the wood fibre insulation boards. (dust extraction, dust mask)

Building moisture

- Wood fibre insulation boards are delivered dry. On building sites a material moisture level is reached that allows immediate plaster coating.
- In the event of prolonged damp weathering with driving rain, or in periods of very high humidity, the material moisture content of the wood fibre insulation boards that have not yet been plastered may increase significantly. Before plastering, a limit moisture content of the wood fibre insulation board of 13 % must be maintained.
- For renovations and new buildings made of mineral building materials a high core moisture content of the substrate must be avoided.

Installation

Installation as a plaster base board

- Under <http://www.steico.com/technical-installation> or the enclosed QR code, you will find the processing instructions for this product under the category „processing instructions STEICO ETICS“.
- (Installation instructions facade insulation)

- This document is based on the German technical data sheet and is intended for general information purposes in an international context. National regulations and building codes must be additionally observed.



Certificates and quality management



☰ Caption

other abbreviations

- pal.** Pallet
- T&G** Tongue and Groove
- pac.** Packaging
- approx.** Approximately
- pcs.** pieces