

STEICO *multi tape black*

High performance tape with special surface



- Solvent-free
- High UV and ageing resistance
- High moisture resistance/rainproof
- Can be used indoors and in protected outdoor areas
- Can be applied from -10 °C (dry and ice-free substrate required)
- Temperature-resistant from -40 to +100 °C

Application area



- Joint and connection bonding of STEICO wood fibre boards in combination with STEICO *multi primer*
- Joint and connection bonding with STEICO *universal black*
- Connection bonding for STEICO *fix* and STEICO *tri* sub-window sills

Technical data

Temperature resistance [°C]	-40 to +100
Processing temperature [°C]	≥ -10; substrate must be dry and free of ice
Minimum roof pitch [°]	10
Adhesive	Acrylic dispersion, solvent-free
Adhesive backing	UV-stabilized special fleece, adhesive on one side
Colour	Black without print
Thickness (without release paer) [mm]	approx. 0,6
UV resistance	6 months (before applying the façade cladding)
Peeling strength	complies with DIN 4108-1
Peel strength after ageing	complies with DIN 4108-11
s _d -value [m]	1,5

Forms of delivery

Length [mm]	Width [mm]	Release liner slashing [mm]	Number/pack. [pcs.]
25000	70	20/50	8
25000	140	50/20/70	4

STEICO *multi tape black*

High performance tape with special surface

Weight and packing

Length [mm]	Width [mm]	Weight/m ² [kg]	Weight/pcs. [kg]	Weight/pack. [kg]	Packaging/pack. Paper/cardboard (approx.) [kg]
25000	70	0.65	0.8	7.50	0.80
25000	140	0.65	1.6	7.50	1.20

Notes

Storage

- Store in a cool and dry place at +5 to +25 °C
- Protect from heat, cold and UV radiation

Ingredients

- Acrylic dispersion (solvent-free), UV-stabilized special fleece

Disposal

- dispose with normal construction waste, observe applicable legal guidelines

Cutting

- Sharp knife or other suitable cutting tool

Installation

Application in the STEICO membrane system

- Substrates must be stable, dry and free of dust and grease.
- Align STEICO *multi tape black*, remove the release paper step by step, and rub the tape down firmly.
- Slit release paper makes it easier to bond corners, as liners can be removed in turn as required.
- Apply STEICO *multi tape black* without tension or creases.
- If tensile forces occur, the substrate must also be mechanically fastened.
- Bonds must not be in standing water. Bonding in sauna and swimming pool construction is also not permitted.

Installation on STEICO wood fibre boards

- Pre-treat STEICO wood fibre boards in the bonding area with STEICO *multi primer*.
- After sufficient flash-off time (if primer is transparent), apply STEICO *multi tape black*, remove release paper and rub on.
- The bonding area per butt joint side must be at least 50 mm.
- To improve adhesion, additional pressing with a paint roller or roofing roller is recommended
- Once the adhesive tape has been applied, it can be plastered over
- Regional and national regulations and Building laws have to be fulfilled

STEICO *multi tape black*

High performance tape with special surface

Certificates and quality management



☰ Caption

other abbreviations

- pal.** Pallet
- T&G** Tongue and Groove
- pac.** Packaging
- approx.** Approximately